

SPECIFICATIONS FOR ASPHALT CURB

820. 1 SCOPE

This work shall consist of constructing asphalt curb to the dimensions and grade as shown on the plans or staked on the ground by the Engineer.

820. 5 MATERIALS

Aggregate shall conform to the requirements of the "Specifications for Aggregate for Bituminous Pavement".

Asphaltic materials will be supplied to the Contractor as set forth in the Special Provisions.

820. 7 CONSTRUCTION METHODS

The surface on which the asphalt curb is to be constructed shall be thoroughly cleaned and a tack coat applied by means of an approved spraying device prior to the placing of the curb.

The asphalt curb shall be extruded to such dimensions that it will have the required cross-section.

The material shall be extruded under pressure to obtain minimum density of 90% of the density obtainable for the same material compacted in the laboratory by the Marshall method.

After the curb material has set, the exposed surfaces shall be sealed with asphalt applied by an approved spraying device. The temperature and rate of application of the asphalt shall be as directed by the Engineer.

820. 9 METHOD OF MEASUREMENT

"Asphalt Curb" will be measured in linear metres along the base of the curb face.

820. 11 BASIS OF PAYMENT

"Asphalt Curb" will be paid for at the contract unit price per linear metre and will be payment in full for the performance of all operations pertaining thereto, as herein described, and those operations incidental to the work.